



B60 Supa Squeeze Tape Data Sheet

Characteristic	Test Result	Test Method
Density	95kg/m ³	BS EN ISO 845
Polymer	Type semi closed cell NBR	
Temperature Range	-10°C/+110°C	
Flammability Rating	Passed	FMVSS302
Compression Deflection @25%	2.8 kPa	BS EN ISO 6916-1
@50%	6.9 kPa	BS EN ISO 6916-1
Compression Set 23°C 22H 50%	<0.8%	BS EN ISO 1856
40°C 22H 50%	<25%	BS EN ISO 1856
Tensile Strength	300 kPa	BS EN ISO 1798
Elongation	<180.6%	BS EN ISO 1798
Tear Resistance	<0.73 kN/m	BS EN ISO 34-1
Linear Shrinkage	<1.2%	BS EN ISO 2796
Dimensional Stability 3H/80°	<1.34%	BS EN ISO 2797
Water Seal	Passed	IN HOUSE
Ozone Resistance	Zero Cracking	DIN 53509-1
UV Air Resistance	Excellent	